

Technical Data Sheet
JAZEERA ANTICARBONATION WB
JA-15051

Description:

A high quality water borne eggshell topcoat paint, based on pure acrylic emulsion. It provides excellent anti-carbonation and alkali resistant topcoat with superior weather resistance and outdoor durability.

Recommended Use:

It can be used as a protective and decorative topcoat for exterior and interior applications on concrete, cement and other masonry substrates for palaces, houses, car parks, bridges, tunnels and coastal areas buildings.

Characteristics:

- Excellent anti-carbonation properties.
- Water vapor permeable.
- Long-lasting corrosion protection to reinforced steel in concrete.
- Excellent adhesion to substrates and high durability.
- Excellent weather, water and UV resistance.
- Excellent resistance to moisture and salts.
- Good resistance to scratch and water.
- Resistance to dirt pick up.
- Excellent color retention.
- Antibacteria inside can.
- Very Low VOC content.
- Free from formaldehyde, ammonia and APEOs.

Physical Constants:

| | | |
|-------------------------------|---|-------------|
| • Finish | Eggshell. | |
| • Color | White and other colors of Jazeera color card. | |
| • Specific Gravity | 1.30 | ASTM D2697. |
| • Viscosity | 97 KU | ASTM D562. |
| • Volume Solid | 40±2 %. | |
| • D.F.T. | 50 - 100 μ, each coat. | |
| • Theoretical Spreading Rate* | 4-8 m ² /L . | |
| • Freeze-Thaw Stability | Pass | ASTM D2243. |

Tests:

| | | | |
|----------------------------------|------------|---------------------------|-----------|
| • VOC content | 45.458 g/L | ASTM D3960:2005 | METS, UAE |
| • VOC Emission After Application | Pass | LEED Requirements - Ver.4 | METS, UAE |

Carbon Dioxide Permeability Test: Tested by Wimpey Laboratories - Dubai - U.A.E.

(BS EN 1062-6:2002 Method A)

| | |
|---|--|
| -Specimen Thickness: | 276μm. |
| -Average Carbon dioxide permeability: | 0.886 g/m ² .d. |
| -Diffusion equivalent air thickness in meter (SD): | 279.91m. |
| -Diffusion resistance number: | 1.01×10 ⁶ . |
| -Carbon dioxide diffusion coefficient of the coating: | 1.47×10 ⁻⁷ cm ² .s ⁻¹ . |
| -Diffusion equivalent of concrete in meter (SC): | 0.966m. |

Classification of coating material and coating systems for exterior masonry and concrete: C1 (DIN EN 1062-1:2004-08).

Technical Data Sheet

JAZEERA ANTICARBONATION WB JA-15051

Surface Preparation:

- All new surfaces shall be cured at least 28 days prior to application of the primer.
- Remove old paints completely from previously painted surfaces.
- The substrate should have sufficient strength and free from unsounded areas, pug holes, protrusions and pops.
- Make sure that the surface is clean, dry, free from dust, oil, grease, salt and mold.
- Fill the holes and cracks with suitable fillers such as "Jazeera Ultimate", "Jazeera Unique Filler" or "Jazeera Epoxy Crack Filler 400" prior to application of the primer (Refer to TSD).

Application Guide:

- The required temperature during application, must not be less than 5°C; the surface moisture should not exceed 8% and the relative humidity at work place should not exceed 70%.
- pH of surface should not exceed 9.
- Paint should be stirred carefully before use.
- A suitable quantity of "Tap Water" can be added to get reasonable viscosity for application.
- Do not apply on wet and moistened surfaces until completely dry.
- Do not apply the next coat unless the previous one is fully dry. Minimum recoating interval time should be followed.

Application Tools:

- Airless spray: Nozzle orifice : 0.015-0.019"
Nozzle pressure : 15 MPa (2100psi)
Spray angle : 40-60 °
- Air spray : Nozzle size: (1.5 - 1.8) mm.
- Roller: Soft and smooth roller
(Recommended type: Dekor Nardeen 8009 - code: 1093)
- Brush: Suitable type.

Thinner:

Tap water.

Thinning Ratio:

- (0 - 10)% by volume for airless spray.
- (15 - 25)% by volume for air spray gun.
- (10-15)% by volume for roller and brush.

All above depends on the weather and application conditions.

Painting System:

- Apply one coat of "Jazeera Royal Prime" or any other suitable type of Al-Jazeera primers, depending on the surface nature and let it to dry.
- Apply two coats or more of "Jazeera Anticarbonation WB".

Drying Time:

Surface dry: 30 min.
Hard dry 4 hours.
Recoating interval 8 hours.(minimum)
----- (maximum).

- Full cure: 7 days.

All above results were tested according to ASTM D5895 @ 25°C.

Technical Data Sheet
JAZEERA ANTICARBONATION WB
JA-15051

Cleaning Tools:

Tap water.

Packing:

- US Gallon. & 18 Ltrs. Drum.
- Gallon: Base 3 Ltr (Tintable).
- Drum: Base 16.2 Ltr (Tintable).

Shelf Life & Storage:

Shelf life : 24 months @ 25 °C.

Storage: The container should be kept in sealed, dry, cool, well -ventilated place and stored in accordance with national regulations.

Safety Precautions:

Please read and follow the precautionary notices displayed on the container, and all caution statements on the MSDS of this product.

- Handle with care before and during use.
- During application of paint, contact of liquid paint with eyes, skin, inhalation of paint mist and paint vapour, should be strongly avoided.
- Recommended to use the product in well-ventilated area when applying the paint in insufficient ventilated areas, forced ventilation should be provided.
- Keep away from the reach of children.

For environmental safety: please donate the leftover paint and packaging to your local authorized institution for usage or recycling purpose.

Note: Wastes and empty containers should be disposed of in accordance with local regulations made under the Control of Pollution Act and the Environmental Protection Act.

Disclaimer:

To the best of our knowledge the technical data listed herein is true and accurate up to publication date and is subject to change without prior notice. User must contact Jazeera Paints Company to verify of any modifications before specifying or ordering the product. Thus, information given in this sheet is not intended to be exhaustive and any person using the product other than the recommendations in this sheet or without reverting to our Jazeera TSD, he should take his accountability in this connection.

As we are not capable to control the quality and the substrate's conditions as well as the factors that affect on using, or applying the product, so we never give any written or implied guarantee in these documents, but we guarantee our products to conform to Jazeera quality while we assume no responsibility for coverage, performance or injuries resulting from application. Liability "if any" is limited to replace the products mentioned above.