

Technical Data Sheet
JAZEERA CHAMOIS
JA-16008

Description:

A high quality water-based decorative paint formulated with a unique blend of acrylic emulsion and special effect pigments, providing a stylish and attractive finish.

Recommended Use:

Recommended to use for interior applications on concrete, cement and gypsum surface for palaces, offices, showrooms, hotels, restaurants, luxurious house entrances, etc.

Characteristics:

- Can be formed in multiple designs.
- Beautiful metallic look.
- Excellent adhesion and high durability.
- Good washability.
- Excellent color retention.

Physical Constants:

• Finish	Sheen	
• Color	As per "Jazeera Chamois" catalog.	
• Specific Gravity	1.07	ASTM D1475
• Viscosity	30 Poise	ASTM D562
• D.F.T	90 μ each coat.	
• Volume Solid	27.20 %.	ASTM D2697
• Theoretical Spreading Rate	3 m ² /lt. @ D.F.T.90 μ .	

Tests:

• Freeze-Thaw Stability	Pass	ASTM D2243
• Heater Stability	Pass	ASTM D2243
• Chemical Resistance	Pass, (Household Chemicals)	ASTM D1308
• Water Resistance	Pass	ASTM D870

*The practical spreading rate of the product depends on the surface, ambient temperature, application method, actual DFT and the wasted amount.

(To avoid waste, be sure to buy the right amount of the paint for the required surface area)

Surface Preparation:

- All new concrete surfaces must be cured at least for 28 days prior to application of the primer.
- For previously painted surfaces remove old paint completely.
- The substrate should have sufficient strength and free from unsounded areas, pug holes, protrusions and pops.
- Make sure that the surface is clean, dry, free from dust, oil, grease, salt, mold.
- Fill the holes and cracks with suitable fillers "Jazeera Ultimate", "Jazeera Unique Filler" and "Jazeera Epoxy Crack Filler 400" prior to application of the primer (Refer to TSD).

Application Guide:

- The required temperature during application, must not be less than 5°C; the surface moisture should not exceed 8% and the relative humidity at work place should not exceed 70%.
- pH of surface should not exceed 9.
- Paint should be stirred carefully before use.
- Do not apply on wet and moistened surfaces until completely dry.
- Do not apply the next coat unless the previous one is fully dry. Minimum recoating interval time should be followed.
- Adequate ventilation should be provided during application time.

Technical Data Sheet
JAZEERA CHAMOIS
JA-16008

Application Tools:

Roller: Soft and smooth woolen roller.

Steel Trowel, Putty knife.

Sea sponge & Normal sponge

Thinner:

Not recommended.

Thinning Ratio:

Ready to use.

Painting System:

- Apply one coat of "Jazeera Green Prime"
- Apply two coats of "Jazeera Green Putty".
- Apply two coats of "Jazeera Silk Deco Primer" with same color of "Jazeera Chamois" and let it to dry.
- Apply one coat of "Jazeera Chamois" by roller then let it (4-6 hours) for drying.
- Apply second coat of "Jazeera Chamois" by special putty knife or trowel to make the required design.
- * Design should be completed within 10 minutes.

Another Application Methode :

Apply one coat of "Jazeera Green Prime"

- Apply two coats of "Jazeera Green Putty".
- Apply one or two coats of "Jazeera Silk Deco Primer" with same color as per its catalog and allow drying.
- Apply "Jazeera Chamois"
 - First color by sea sponge.
 - Second color by sea sponge.
 - Third color by sea sponge.
- Touch softly by normal sponge to give smooth surface.

Drying Time:

- Surface dry (15 - 20) minutes.
- Recoating interval 4-6 hours.
- Hard dry 24 hours.
- Full cure 7 days.

All above test results according to ASTM D5895@25°C.

Cleaning Tools:

Tap water.

Packing:

US Gallon 3.65 L.

Can 0.9L.

Shelf Life & Storage:

Shelf life : 24 months @ 25 °C.

Storage: The container should be kept in sealed, dry, cool, well ventilated place and stored in accordance with national regulations.

Technical Data Sheet
JAZEERA CHAMOIS
JA-16008

Safety Precautions:

Please read and follow the precautionary notices displayed on the container, and all caution statements on the MSDS of this product.

- Handle with care before and during use.
- During application of paint, contact of liquid paint with eyes, skin, inhalation of paint mist and paint vapour, should be strongly avoided.
- Recommended to use the product in well-ventilated area when applying the paint in insufficient ventilated areas, forced ventilation should be provided.
- Keep away from the reach of children.

For environmental safety: please donate the leftover paint and packaging to your local authorized institution for usage or recycling purpose.

Disclaimer:

To the best of our knowledge the technical data listed herein is true and accurate up to publication date and is subject to change without prior notice. User must contact Jazeera Paints Company to verify of any modifications before specifying or ordering the product. Thus, information given in this sheet is not intended to be exhaustive and any person using the product other than the recommendations in this sheet or without reverting to our Jazeera TSD, he should take his accountability in this connection.

As we are not capable to control the quality and the substrate's conditions as well as the factors that affect on using, or applying the product, so we never give any written or implied guarantee in these documents, but we guarantee our products to conform to Jazeera quality while we assume no responsibility for coverage, performance or injuries resulting from application. Liability "if any" is limited to replace the products mentioned above.