

## Technical Data Sheet

### JAZEERA FIREDAMP 263

#### JI-35003

#### Description:

A high quality, high solid acrylic solvent based fire proofing intumescent coating, provides cellulosic fire protection up to 2 hours for steel surfaces.

#### Recommended Use:

It is recommended to use as a fireproofing paint on structural steelworks like beams, columns and hollow sections by protecting from cellulosic fire up to 2 hours

#### Characteristics:

- Provides safety for lives & properties.
- Cellulosic fire protection up to 2 hours for structural steel constructions.
- Excellent flame spread resistance.
- Fast drying & rapid recoatable.
- Suitable for application in the ready steel fabrication.
- High resistance to impact and abrasion.

#### Certificates:

- The product has been approved by the Saudi Civil Defense.
- Tested and certified by Warringtonfire in accordance with BS476: Parts 20/21 - Certificate of Approval No CF10176
- Classified as class1 of flame spread resistance according to ASTM E84 (Exova).

#### Physical Constants:

• Finish:	Matt	
• Color:	White.	
• Volume Solid:	75%	ASTM D2697
• Viscosity:	50 poise @ 31°C	ASTM D562
• Specific Gravity:	1.37 @ 25°C	ASTM D1475
• DFT:	210 to 750 microns per coat.	
• Theoretical Spreading Rate:	3.5-1 m <sup>2</sup> /L @ 210-750 μm DFT.	

#### Tests:

• VOC content	310 g/L	ISO 11890-2:2020	METS, UAE
• VOC Emission After Application	Pass	LEED Requirements - Ver.4	METS, UAE
• Flame Spread Resistance:	Class1	ASTM E84	Exova Warringtonfire
• Abrasion Resistance:	Pass	ASTM D4060-10	Wimpey Laboratory - U.A.E.
• Impact Resistance:	Pass	ASTM D2794	Wimpey Laboratory - U.A.E.
• Hardness	78±2 Shore D	ASTM D2240	SASO

#### Surface Preparation:

##### PRE-CLEANING:

- Remove all visible surface deposits such as grease, oils and soils with suitable detergent. Remove salt and other contaminants by washing using high pressure fresh water.
- Where necessary, work to remedy or alleviate design or fabrication defects such as weld spatter, and where required smooth weld seams and sharp edges before abrasive blasting.

##### NEW STEEL:

- Refer to pre-cleaning, the surface must be prepared according to Sa 2½ (NACE No.2/SSPC-SP 10) or Sa 2 (NACE No. 3/SSPC-SP 6) .

#### Application Condition:

- Temperature during application should be more than (5°C).
- Surface temperature: at least (3°C) above dew point.
- Relative humidity: maximum 85%.

## Technical Data Sheet

### JAZEERA FIREDAMP 263

#### JI-35003

#### Painting System:

- Primers: Jazeera Epoxy Zinc Phosphate Primer.
- Topcoats: Jazeera Firedamp 263.

For protection & colored appearance apply: "Jazeera Firedamp 275" as a topcoat.

#### Application Method and Thinning:

"Jazeera Thinner 507" can be used if necessary, or consult TSD.

Application Method	Airless Spray	Brush/Roller
Thinning (by volume)*	(0) %	(5)%
Nozzle Orifice	17-25 (inch/1000)	N/A
Nozzle Pressure	240 bar (approx.3480 psi)	N/A

#### Drying Time and Recoating:

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly.

Temperature	25°C/77°F
Relative humidity	50%
Surface dry	30 minutes
Dry to recoat, minimum	4 hours
Dry to recoat, maximum*	Extended
Dry to service	14 days.

Note: All records given in the table are typical at: recommended film thickness, good ventilation and one coat system.

\*The surface should be dry and clean prior to application. The best time to recoat is before previous coat is cured. If this time is exceeded, the surface may need to be roughened slightly.

#### Limitations:

- \* Finish depends on the method of application. For aesthetic look, surface must be prepared once again before applying topcoat.
- \* Jazeera Firedamp 263 should be protected from water immersion or running water.

#### Packing:

Drum : 18 Ltr .

#### Shelf Life & Storage:

- Shelf life : 24 months @ 25 °C.
- Storage: The container should be kept in sealed, dry, cool, well ventilated place and stored in accordance with national regulations.

**Technical Data Sheet**  
**JAZEERA FIREDAMP 263**  
**JI-35003**

---

**Handling and Safety:**

- Clean up: Use "Jazeera Thinner 507" for tools cleaning and in case of spillage, absorb and dispose.
- Handling: Handle with care. Stir very well before use.
- Health and safety: Please read and follow the precautionary notices displayed on the container, and all caution statements on the MSDS of this product. During application of paint, contact of liquid paint with eyes, skin, inhalation of paint mist and paint vapor should be strongly avoided. For spray application systems; applicator should wear protective clothing, gloves, also eye, skin and respiratory protection are always recommended. Keep away from reach of children.
- Ventilation: When used in enclosed areas, thorough air circulation must be used during and after application until the coating is cured. In addition, respirators must be used by all applicator.
- Caution: This product contains flammable solvents, keep away from sparks and open flame. For information on LEL and TLV, please read the MSDS.
- Environmental safety: Please donate the leftover paint and packaging to your local authorized institution for usage or recycling purpose.
- Note: Wastes and empty containers should be disposed of in accordance with local regulations made under the Control of Pollution Act and the Environmental Protection Act.

**Disclaimer:**

To the best of our knowledge the technical data listed herein is true and accurate up to publication date and is subject to change without prior notice. User must contact Jazeera Paints Company to verify of any modifications before specifying or ordering the product. Thus, information given in this sheet is not intended to be exhaustive and any person using the product other than the recommendations in this sheet or without reverting to our Jazeera TSD, he should take his accountability in this connection.

As we are not capable to control the quality and the substrate's conditions as well as the factors that affect on using, or applying the product, so we never give any written or implied guarantee in these documents, but we guarantee our products to conform to Jazeera quality while we assume no responsibility for coverage, performance or injuries resulting from application. Liability "if any" is limited to replace the products mentioned above.