

## Technical Data Sheet

### JAZEERA FIREDAMP W3

#### JA-14013

#### Description:

A high quality, fire proofing water-borne intumescent coating formulated without halogens and low VOC, designed for protection of structural steels from cellulosic fire.

#### Recommended Use:

It is recommended to use as a fireproofing paint on structural steelworks like beams, columns and hollow sections by protecting from cellulosic fire up to 4 hours

#### Characteristics:

- Fire resistance up to 4 hours.
- Flame spread resistance.
- Halogens-free.
- Very low VOC.

#### Certificates:

- Tested and certified by Warringtonfire in accordance with BS476: Parts 20/21 - Certificate of Approval No CF10166

#### Physical Constants:

• Finish:	Matt	
• Colors:	White.	
• Volume Solids:	70 %	
• Viscosity:	135 KU @ 25°C	ASTM D562
• Specific Gravity:	1.38	ASTM D1475
• Flash Point:	>101°C (>214 °F)	
• DFT:	210 to 700 microns per coat.	
• Theoretical Spreading Rate:	3.3 - 1 m <sup>2</sup> /L @ 210-700 microns DFT	

#### Tests:

• VOC:	2.52 g/L	ASTM D2369	METS - UAE
• Flame Spread Resistance:	Class1	ASTM E84	Exova Warringtonfire
• VOC Emission After Application	Pass	Leed Requirements - Ver.4	METS - UAE
• Compressive Strength:	11.6 N/mm <sup>2</sup>	ASTM D695-10	Wimpey Laboratory - UAE
• Corrosion Resistance:	Pass Class C4 / V. High	ISO 12944-6:2018	Wimpey Laboratory - UAE
• Hardness, Shore A:	64	ASTM D2240-15	Wimpey Laboratory - UAE
• Tensile Strength:	11.8 MPa	ASTM D638-14	Wimpey Laboratory - UAE
• Chemical Resistance:	Pass	ISO 2812-1	Wimpey Laboratory - UAE
• Heat Deflection Temperature:	52.1°C	ASTM D648:2007 Method A	Wimpey Laboratory - UAE

#### Surface Preparation:

##### PRE-CLEANING:

- Remove all visible surface deposits such as grease, oils and soils with suitable detergent. Remove salt and other contaminants by washing using high pressure fresh water.
- Where necessary, work to remedy or alleviate design or fabrication defects such as weld spatter, and where required smooth weld seams and sharp edges before abrasive blasting.

##### NEW STEEL:

- Refer to pre-cleaning, the surface must be prepared according to Sa 2½ (NACE No.2/SSPC-SP 10) or Sa 2 (NACE No. 3/SSPC-SP 6) .



## Technical Data Sheet

### JAZEERA FIREDAMP W3

### JA-14013

#### Application Condition:

- Temperature during application should be more than (5°C).
- Surface temperature: at least (3°C) above dew point.
- Relative humidity: maximum 85%.

#### Painting System:

- Primers: Jazeera Epoxy Zinc Phosphate Primer , or consult Jazeera TS Team.
- Topcoats: Jazeera Firedamp W3.

For protection & colored appearance apply "Jazeera Firedamp 275" as a topcoat for exterior applications.

#### Application Method and Thinning:

"Tap water" can be used if necessary, or consult TSD.

Application Method	Airless Spray	Brush/Roller
Thinning (by volume)*	Not recommended	5 %
Nozzle Orifice	17-25 (inch/1000)	N/A
Nozzle Pressure	220 bar (approx.3190 psi)	N/A

#### Drying Time and Recoating:

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly.

- Temperature 25°C/77°F
- Relative humidity 50%
- Surface dry 2 hours
- Dry to recoat, minimum 8 hours
- Dry to recoat, maximum\* -----
- Dry to service 14 days.

Note: All records given in the table are typical at recommended film thickness, good ventilation and one coat system.

\*The surface should be dry and clean prior to application. The best time to recoat is before previous coat is cured. If this time is exceeded, the surface may need to be roughened slightly.

#### Limitations:

- Level of surface finish is dependent on application method. Avoid using a mixture of application methods whenever possible.
- Highly decorative finish is possible if properly prepared before top coating.
- Over-application will extend both the minimum over coating periods and handling times.
- 'Firedamp W3' must be protected from Freezing at all times (storage & transportation).
- Coating (with or without topcoat) must be protected from running water & frequent water immersion.

#### Packing:

Drum : 18 Ltr .

#### Shelf Life & Storage:

- Shelf life : 12 months @ 25 °C.
- Storage: The container should be kept in sealed, dry, cool, well ventilated place and stored in accordance with national regulations.

**Technical Data Sheet**  
**JAZEERA FIREDAMP W3**  
**JA-14013**

---

**Handling and Safety:**

- Clean up: Use "Clean Water" for tools cleaning and in case of spillage, absorb and dispose.
- Handling: Handle with care. Stir very well before use.
- Health and safety: Please read and follow the precautionary notices displayed on the container, and all caution statements on the MSDS of this product. During application of paint, contact of liquid paint with eyes, skin, inhalation of paint mist and paint vapor should be strongly avoided. For spray application systems; applicator should wear protective clothing, gloves, also eye, skin and respiratory protection are always recommended. Keep away from reach of children.
- Ventilation: When used in enclosed areas, thorough air circulation must be used during and after application until the coating is cured. In addition, respirators must be used by all applicator.
- Environmental safety: Please donate the leftover paint and packaging to your local authorized institution for usage or recycling purpose.
- Note: Wastes and empty containers should be disposed of in accordance with local regulations made under the Control of Pollution Act and the Environmental Protection Act.

**Disclaimer:**

To the best of our knowledge the technical data listed herein is true and accurate up to publication date and is subject to change without prior notice. User must contact Jazeera Paints Company to verify of any modifications before specifying or ordering the product. Thus, information given in this sheet is not intended to be exhaustive and any person using the product other than the recommendations in this sheet or without reverting to our Jazeera TSD, he should take his accountability in this connection. As we are not capable to control the quality and the substrate's conditions as well as the factors that affect on using, or applying the product, so we never give any written or implied guarantee in these documents, but we guarantee our products to conform to Jazeera quality while we assume no responsibility for coverage, performance or injuries resulting from application. Liability "if any" is limited to replace the products mentioned above.