

Technical Data Sheet

JAZEERA R.O PRIMER

JI-71001

Description:

A high quality alkyd primer, anti-corrosive, based on iron red oxide (rust inhibitive pigment) for atmospheric exposure.

Recommended Use:

Recommended to use as a primer for exterior and interior applications in a wide range of industrial structures on steelworks, such as warehouses, steel structures, doors and fire fighting systems.

Characteristics:

- Good resistance to corrosion.
- Very good adhesion.
- Good resistant to weather conditions.

Physical Constants:

• Finish	Flat		
• Color	Red		
• Volume Solid	55%	ASTM D2697	
• Viscosity	87 KU @25°C	ASTM D562	
• Specific Gravity	1.58	ASTM D1475	
• DFT	40 µ each coat		
• Theoretical Spreading Rate	13.75 m ² /L @ D.F.T. 40 µm.		

Tests:

• VOC	336.46 g/L.		
• MPI	Meets Standard # 79		
• Opacity	99.4%	ASTM D2805	Wimpey Laboratories-U.A.E.
• Adhesion	3.41 N/mm ²	ASTM D4541	Wimpey Laboratories-U.A.E.

Surface Preparation:

- Remove all visible surface deposits such as grease, oils with suitable detergent per (SSPC-SP1).
- Remove salt and other contaminants by washing using high pressure fresh water.
- Any fabrication defects such as weld spatter, delamination, sharp edges and weld slag should be repaired prior to surface preparation.

Steel Surfaces:

- The surface must be prepared according to Sa 2½ (ISO 8501-1)- (NACE No.2/SSPC-SP10), or Sa2 (NACE No.3/SSPC-SP6) or hand and power tool cleaning according to St3(SSPC-SP3).

Application Conditions:

- Temperature during application should be more than (5°C).
- Surface temperature: at least (3°C) above dew point.
- Relative humidity: maximum 85%.

Painting System :

Primers: Jazeera R.O Primer.

Topcoats: Overcoated with all kinds of alkyd paints.

Technical Data Sheet
JAZEERA R.O PRIMER
JI-71001

Application Method and Thinning:

THINNER: "Jazeera Thinner 504".

Application Method	Airless Spray	Air Spray	Brush/Roller**
Thinning (by volume)*	(0-5)%	(20-25) %	(10-15)%
Nozzle Orifice	0.015-0.021"	1.5- 1.8 mm	N/A
Nozzle Pressure	15 MPa (2100psi)	29.0-43.5 psi	N/A
Spray Angle	40°-80°	50°-80°	N/A

* Depends on the weather condition at work place.

** Recommended for stripe coat and small areas.

Film Thickness and Spreading Rate:

	Minimum		Maximum		Recommended	
	(μm)	mil	(μm)	mil	(μm)	mil
Dry Film Thickness (DFT)	25	1	75	3	40	1.6
Wet Film Thickness (WFT)	46	1.85	136	5.44	73	2.9
	m ² /l	ft ² /USgal	m ² /l	ft ² /USgal	m ² /l	ft ² /US gal
Theoretical Spreading Rate	22	882	7.33	294	13.75	551

Drying Time and Recoating:

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly.

Temperature	25°C/77°F
Relative humidity	50%
Surface dry	1 hour
Hard dry	8 hours
Dry to recoat, minimum	4.5 hours @ 45°C
Dry to recoat, maximum*	-----
Full cure	7 days

Note: All records given in the table are typical at: recommended film thickness, good ventilation and one coat system.

*The surface should be dry and clean prior to application. The best time to recoat is before previous coat is cured. If this time is exceeded, the surface may need to be roughened slightly.

Packing:

Packed in: US Gallon
Drum 16 L

Shelf Life & Storage:

Shelf life : 12 months @ 25 °C.

Storage: The container should be kept in sealed, dry, cool, well ventilated place and stored in accordance with national regulations.

Technical Data Sheet
JAZEERA R.O PRIMER
JI-71001

Handling and Safety:

- Clean up: Use "Jazeera Thinner 504" for cleaning tools and in case of stains while application.
- Handling: Handle with care. Stir very well before use.
- Health and safety: Please read and follow the precautionary notices displayed on the container, and all caution statements on the MSDS of this product. During application of paint, contact of liquid paint with eyes, skin, inhalation of paint mist and paint vapor should be strongly avoided. For spray application systems; applicator should wear protective clothing, gloves, also eye, skin and respiratory protection are always recommended. Keep away from reach of children.
- Ventilation: When used in enclosed areas, thorough air circulation must be used during and after application until the coating is cured. In addition, respirators must be used by all applicator.
- Caution: This product contains flammable solvents, keep away from sparks and open flame. For information on LEL and TLV, please read the MSDS.
- Environmental safety: Please donate the leftover paint and packaging to your local authorized institution for usage or recycling purpose.
- Note: Wastes and empty containers should be disposed of in accordance with local regulations made under the Control of Pollution Act and the Environmental Protection Act.

Disclaimer:

To the best of our knowledge the technical data listed herein is true and accurate up to publication date and is subject to change without prior notice. User must contact Jazeera Paints Company to verify of any modifications before specifying or ordering the product. Thus, information given in this sheet is not intended to be exhaustive and any person using the product other than the recommendations in this sheet or without reverting to our Jazeera TSD, he should take his accountability in this connection. As we are not capable to control the quality and the substrate's conditions as well as the factors that affect on using, or applying the product, so we never give any written or implied guarantee in these documents, but we guarantee our products to conform to Jazeera quality while we assume no responsibility for coverage, performance or injuries resulting from application. Liability "if any" is limited to replace the products mentioned above.