



Technical Data Sheet

JAZEERA WOOD LACQUER

JI-18006

Description:

One component acrylic solvent based clear topcoat. It provides fully transparent gloss finish appearance and smooth touch.

Recommended Use:

Recommended to use for interior applications as a clear gloss topcoat on wooden surfaces such as doors, windows and furniture.

Characteristics:

- Excellent non-yellowing property.
- Very good gloss retention.
- High transparency.
- Very fast drying.

Physical Constants:

• Finish:	Gloss.	
• Gloss:	Above 80 at 60°, ASTM D-523.	
• Color:	Clear.	
• Volume Solid:	33 %.	ASTM D2697.
• Viscosity:	55 KU @ 25 °C	ASTM D562.
• Specific Gravity:	0.95 @ 25 °C	ASTM D1475.

Tests:

• Hardness:	Pass, 4 H Pencil	ASTM D3363.
• Scratch Resistance:	Pass, 1 Kg.	ASTM D5178.
• Bending:	No failure up to 3 mm. Diameter	ASTM D522.
• Adhesion:	No remove	ASTM D3359.
• Water Resistance:	No failure	ASTM D870.
• Flash Point:	Above 23°C.	

Surface Preparation:

Remove all visible surface deposits such as grease, oils, dust, soils, salt and other contaminants. Make the surface smooth by sanding with sand paper and clean it well.

Application Conditions:

- Temperature during application should be more than (5°C).
- Surface temperature: at least (3°C) above dew point.
- Relative humidity: maximum 85%.

Paint System:

Primers:

- For natural wood appearance, apply **Jazeera Wood Sealer**.
- For colored wood appearance, apply "**Jazeera Wood Stain**" before sealer.

Topcoats:

- **Jazeera Wood Lacquer**.

Application Methods and Thinning:

Thinner: Thinner: Recommended thinner is "**Jazeera Thinner 507**".

Application Method	Airless Spray	Air Spray	Brush/Roller
• Thinning (by volume)*	(0-5)%	(25-30)%	(10-15)%
• Nozzle Orifice	0.011-0.015"	(1.5-1.8) mm	N/A
• Nozzle Pressure	6.5 MPa (910psi)	29.0-43.5 psi	N/A
• Spray Angle	40-65°	50-80°	N/A

*Depends on the weather condition at work place.

** Recommended for stripe coat and small areas.

Technical Data Sheet
JAZEERA WOOD LACQUER
Jl-18006

Film Thickness and Spreading Rate:

	Minimum		Maximum		Recommended	
	(μm)	mil	(μm)	mil	(μm)	mil
• Dry Film Thickness (DFT)	20	0.8	50	2	30	1.2
• Wet Film Thickness (WFT)	61	2.44	152	6	91	3.64
	m^2/l	ft^2/USgal	m^2/l	ft^2/USgal	m^2/l	ft^2/USgal
• Theoretical Spreading Rate	16.5	661.7	6.6	264.7	11	441.1

Drying Time:

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly.

- Temperature 25°C/77°F
- Relative Humidity 50%
- Surface Dry 15-20 min.
- Hard Dry 1 hour
- Full Cure 7 days
- Dry to recoat, minimum 2 hours
- Dry to recoat, maximum* -----

Note: All records given in the table are typical at: recommended film thickness, good ventilation and one coat system.

*The surface should be dry and clean prior to application. If the recoating interval is exceeded, the surface may need to be roughened

Packing:

Packed in: Gallon 3.6 liters

Storage and Shelf Life:

Shelf life : 24 months @ 25 °C.

Storage: Store indoors. Storage conditions are to keep the container in sealed container in dry, cool and well ventilated place.

Handling and Safety:

- Cleanup: Use **Jazeera Thinner 507** for tools cleaning and in case of spillage, absorb and dispose.
- Handling: Handle with care. Stir very well before use.
- Health and Safety: Please read and follow the precautionary notices displayed on the container, and all caution statements on the MSDS of this product. During application of paint, contact of liquid paint with eyes, skin, inhalation of paint mist and paint vapor should be strongly avoided. For spray application systems; applicator should wear protective clothing, gloves, also eye, skin and respiratory protection are always recommended. Keep away from reach of children.
- Ventilation: When used in enclosed areas, thorough air circulation must be used during and after application until the coating is cured. In addition, respirators must be used by all applicator.
- Caution: This product contains flammable solvents, keep away from sparks and open flame. For information on LEL and TLV, please read the MSDS.
- Environmental safety: Please donate the leftover paint and packaging to your local authorized institution for usage or recycling purpose.
- Notes: Wastes and empty containers should be disposed of in accordance with local regulations made under the Control of Pollution Act and the Environmental Protection Act.

Disclaimer:

To the best of our knowledge the technical data listed herein is true and accurate up to publication date and is subject to change without prior notice. User must contact Jazeera Paints Company to verify of any modifications before specifying or ordering the product. Thus, information given in this sheet is not intended to be exhaustive and any person using the product other than the recommendations in this sheet or without reverting to our Jazeera TSD, he should take his accountability in this connection.

As we are not capable to control the quality and the substrate's conditions as well as the factors that affect on using, or applying the product, so we never give any written or implied guarantee in these documents, but we guarantee our products to conform to Jazeera quality while we assume no responsibility for coverage, performance or injuries resulting from application. Liability "if any" is limited to replace the products mentioned above.