

Technical Data Sheet JAZEERA METALO JI-38009

Description:

A high quality plian pearlescent decorative topcoat paint, solvent borne, single component, based on special acrylic resin with resistance to the harsh weather conditions in the Middle East.

Recommended Use:

Recommended to use for exterior and interior applications for all metallic and wooden works like home, office furniture as well as doors.

Characteristics:

- Plain pearlscent appearance.
- Very good resistance to weather conditions.
- Excellent color and gloss retention.
- Very good resistance to UV.
- · Fast drying.
- · Non-yellowing.
- Very good resistance to scratch.

Physical Constants:

| , o.cat oootato. | | | | | |
|----------------------------|-------------------------------------|--------------------|--|--|--|
| • Color | As per Jazeera Metalo catalog. | | | | |
| Volume Solid | 33% | ASTM D 2697 | | | |
| Viscosity | 85 KU @ 25ºC | ASTM D 562 | | | |
| Specific Gravity | 0.97 | ASTM D 1475 | | | |
| • D.F.T | 50 μ each coat | | | | |
| Theoretical Spreading Rate | 6.6 m²/ L at 50 μ DFT | | | | |
| • VOC | 605 g/ L. | | | | |

Surface Preparation:

- $\bullet \ \ \text{Remove all visible surface deposits such as grease, oils with suitable detergent per (\textbf{SSPC-SP1}).}$
- \bullet Remove salt and other contaminants by washing using high pressure fresh water.
- Any fabrication defects such as weld spatter, delamination, sharp edges and weld slag should be repaired prior to surface preparation.
- The surface must be prepared according to Sa 2½ (NACE No.2/SSPC-SP10).
- For improved adhesion, "Jazeera Metalo" should be applied when the undercoat is still tacky. On cured undercoats, adhesion will be enhanced by sweep-blasting the substrate.

Application Condition:

- Temperature during application should be more than (5°C).
- Surface temperature: at least (3°C) above dew point.
- Relative humidity: maximum 85%.

Painting System:

Primers:

- For metallic works:

Epoxy Primer: (Jazeera Epoxy Zinc Phosphate Primer) or (Jazeera Epoxy Red Oxide Primer).

Acrylic Primer: (Jazeera Steelo Primer).

Alkyd Primer: (Jazeera Zinc Phosphate Primer QD) or (Jazeera Red Oxide Primer QD).

- For wooden works:

Jazeera Wood Rak Sanding Sealer

Topcoat: Jazeera Metalo.

Page: 1 / 3 Issued: 2021



Technical Data Sheet JAZEERA METALO JI-38009

Application Method And Thinning:

Thinner: "Jazeera Thinner 507".

| Application Method | Airless Spray | Air Spray | Brush/Roller** |
|-------------------------|---------------|---------------------------|----------------|
| • Thinning (by volume)* | | (15-20) % | (5-10)% |
| Nozzle Orifice | | 1.5- 1.8 mm | N/A |
| Nozzle Pressure | | 29.0-43.5 psi | N/A |
| Spray Angle | | 50-80 ⁰ | N/A |

[•] Depends on the weather condition at work place.

Film Thickness and Spreading Rate:

| | Min | imum | num Maximum | | Recommended | |
|-----------------|------|-----------|---------------|-----------|---------------|------------|
| | (µm) | mil | (μ m) | mil | (μ m) | mil |
| Dry Film | | | | | | |
| Thickness (DFT) | 30 | 1.2 | | | 50 | 2 |
| Wet Film | | | | | | |
| Thickness (WFT) | 91 | 3.6 | | | 150 | 6 |
| | m²/l | ft²/USgal | m²/I | ft²/USgal | m²/l | ft²/US gal |
| Theoretical | | | | | | |
| Spreading Rate | 11 | 441 | | | 6.6 | 265 |

Drying Time And Recoating:

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly.

Temperature 25°C/77°F
Relative humidity 55%
Surface dry 20 minutes.
Hard dry 4 hours
Dry to recoat, minimum 4 hours
Dry to recoat, maximum*
Full cure 7 days

Note: All records given in the table are typical at: recommended film thickness, good ventilation and one coat system.

*The surface should be dry and clean prior to application. The best time to recoat is before previous coat is cured. If this time is exceeded, the surface may need to be roughened slightly.

Packing:

Packing: Packed in 1L

Shelf Life & Storage:

Shelf life: 12 months @ 25 °C.

Storage: The container should be kept in sealed, dry, cool, well ventilated place and stored in accordance with national regulations.

Page: 2/ 3 Issued: 2021

[•] Recommended for stripe coat and small areas.



Technical Data Sheet JAZEERA METALO JI-38009

Safety Precautions:

- Clean up: Use "Jazeera Thinner 507" for tools cleaning and in case of spillage, absorb and dispose.
- Handling: Handle with care. Stir very well before use.
- Health and safety: Please read and follow the precautionary notices displayed on the container, and all caution statements on the MSDS of this product.
- During application of paint, contact of liquid paint with eyes, skin, inhalation of paint mist and paint vapor should be strongly avoided.
- For spray application systems; applicator should wear protective clothing, gloves, also eye, skin and respiratory protection are always recommended. Keepaway from reach of children.
- Ventilation: When used in enclosed areas, thorough air circulation must be used during and after application until the coating is cured. In addition, respirators must be used by all applicator.
- Caution: This product contains flammable solvents, keep away from sparks and open flame. For information on LEL and TLV, please read the MSDS.

Environmental

- Safety: Please donate the leftover paint and packaging to your local authorized institution for usage or recycling purpose.
- Note: Wastes and empty containers should be disposed of in accordance with local regulations made under the Control of Pollution Act and the Environmental Protection Act.

Disclaimer:

To the best of our knowledge the technical data listed herein is true and accurate up to publication date and is subject to change without prior notice. User must contact Jazeera Paints Company to verify of any modifications before specifying or ordering the product. Thus, information given in this sheet is not intended to be exhaustive and any person using the product other than the recommendations in this sheet or without reverting to our Jazeera TSD, he should take his accountability in this connection.

As we are not capable to control the quality and the substrate's conditions as well as the factors that affect on using, or applying the product, so we never give any written or implied guarantee in these documents, but we guarantee our products to conform to Jazeera quality while we assume no responsibility for coverage, performance or injuries resulting from application. Liability "if any" is limited to replace the products mentioned above.

Page: 3 / 3 Issued: 2021