

Technical Data Sheet

JAZETAL UNDER COAT

JA-31001

Description:

A superior quality undercoat paint based on modified alkyd resin. It is characterized by close pores and strong adhesion. It can be used directly on wood or as an intermediate coat on concrete and steelworks where smooth surface is required.

Recommended Use:

Recommended to use for interior and exterior applications on various substrates like wood, fiber glass boards, and sealed masonry surfaces, in industrial workshops, commercial areas and residential buildings.

Characteristics:

- Excellent adhesion.
- Superior hiding.
- Gives smooth surface that insure quality finish of topcoat.
- Very good sealing property.
- Lead free.

Physical Constants:

• Finish	Matt.	
• Color	White.	
• Specific Gravity	1.50	ASTM D1475.
• Viscosity	100 KU	ASTM D562.
• Volume Solid	54 %	ASTM D2697.
• D.F.T	40 μ . Each coat.	
• Theoretical Spreading Rate*	13.5 m ² /L @ D.F.T 40 μ .	
• Adhesion	Pass	ASTM D3359.
• Water Resistance	Pass	ASTM D870.
• Flash Point	38°C.	
• VOC	364 g/L.	

*The practical spreading rate of the product depends on the surface, ambient temperature, application method, actual DFT and the wasted amount.

(To avoid waste, be sure to buy the right amount of the paint for the required surface area).

Surface Preparation:

For Concrete Surfaces:

- All new surfaces shall be cured at least 28 days prior to application of the primer.
- Remove old paints completely from previously painted surfaces .
- The substrate should have sufficient strength and free from unsounded areas, pug holes, protrusions and pops.
- Make sure that the surface is clean, dry, free from dust, oil, grease, salt and mold .
- Fill the holes and cracks with suitable fillers such as "Jazeera Ultimate", "Jazeera Unique Filler" or "Jaz Epoxy Crack Filler ESP" prior to application of the primer (Refer to TSD).

For Wooden Surfaces:

- Remove all visible surface deposits such as grease, oils, dust, soils, salt and other contaminants.
- Make the surface smooth by sanding with sand paper and clean it well prior to application.

Technical Data Sheet
JAZETAL UNDER COAT
JA-31001

Application Guide:

- The required temperature during application, must not be less than 5°C; the surface moisture should not exceed 8% and the relative humidity at work place should not exceed 70%.
- pH of surface should not exceed 9.
- Paint should be stirred carefully before use.
- A suitable quantity of "Jazeera Thinner 504" can be added to get reasonable viscosity for application.
- Do not apply on wet and moistened surfaces until completely dry.
- Do not apply the next coat unless the previous one is fully dry. Minimum recoating interval time should be followed.
- Adequate ventilation should be provided during application.

Application Tools :

- Air spray : Nozzle size: (1.5 – 1.8) mm.
- Roller: Soft and smooth roller
(Recommended type: Dekor Nardeen 8009 - code: 1093)
- Brush: Suitable type.

Thinner:

- Jazeera Thinner 504.

Thinning Ratio:

- 5-10 % By volume for roller/brush.
 - 15-20 % By volume for air spray.
- Depending on weather and application conditions.

Painting System:

For concrete surfaces:

- Apply one coat of "Jazeera Green Prime"
- Apply two coats of "Jazeera Green Putty".
- Apply one coat of "Jazetal Under Coat".
- Apply any suitable architectural paint from Jazeera Paints.

For wooden surfaces:

- Apply one coat of "Jazetal Under Coat".
- Apply any suitable wood paint from Jazeera Paints.

Drying Time:

- Surface dry 2 hours.
- Hard dry 16 hours.
- Recoating interval 16 hours. (minimum)
- Full cure 7 days.

The entire above test reports according to ASTM D5895@25°C.

Cleaning Tools:

- Jazeera Thinner 504 .

Packing:

USG.
Drum: 18 Ltr.

Technical Data Sheet
JAZETAL UNDER COAT
JA-31001

Shelf Life & Storage:

Shelf life : 12 months @ 25 °C.

Storage: The container should be kept in sealed, dry, cool, well -ventilated place and stored in accordance with national regulations.

Safety Precautions:

- Please read and follow the precautionary notices displayed on the container, and all caution statements on the MSDS of this product.
- Handle with care before and during use.
- During application of paint, contact of liquid paint with eyes, skin, inhalation of paint mist and paint vapour, should be strongly avoided.
- Recommended to use the product in well-ventilated area when applying the paint in insufficient ventilated areas, forced ventilation should be provided.
- Keep away from the reach of children.

For environmental safety: please donate the leftover paint and packaging to your local authorized institution for usage or recycling purpose.

Note: Wastes and empty containers should be disposed of in accordance with local regulations made under the Control of Pollution Act and the Environmental Protection Act.

Disclaimer:

To the best of our knowledge the technical data listed herein is true and accurate up to publication date and is subject to change without prior notice. User must contact Jazeera Paints Company to verify of any modifications before specifying or ordering the product. Thus, information given in this sheet is not intended to be exhaustive and any person using the product other than the recommendations in this sheet or without reverting to our Jazeera TSD, he should take his accountability in this connection.

As we are not capable to control the quality and the substrate's conditions as well as the factors that affect on using, or applying the product, so we never give any written or implied guarantee in these documents, but we guarantee our products to conform to Jazeera quality while we assume no responsibility for coverage, performance or injuries resulting from application. Liability "if any" is limited to replace the products mentioned above.