

Technical Data Sheet
JAZ ANTI-FOULING CLASSICO (ESP)
JM-35004

Description:

A high-build, high-solids self-polishing antifouling, based on copolymer reinforced with extra biocide compounds. It has self-erodible effect that maintains an effective surface during its entire service life, providing smoothness to surfaces .

Recommended Use:

- Recommended to use under water line for ships and boats operated at a low or medium speed.
- The actual selection is always based on the input of the operational parameters only

Characteristics:

- TBT Free (It complies with the international convention on the Control of Harmful Antifouling Systems as adopted by IMO 2001)
- Excellent antifouling properties.
- Self-polishing property keeps surface clean and smooth
- Long-lasting service.
- Suitable for upgrading the antifouling system on old ships & boats without costly surface preparation.

Certificates:

- Certified for its performance by Poseidon - SHMRC of New York, USA.

Physical Constants:

• Finish:	Flat	
• Color:	Standard colors as per product's catalog.	
• Volume Solid:	53%.	ASTM D2697
• Viscosity:	85 KU @25°C,	ASTM D562
• Specific Gravity:	1.62	ASTM D1475
• Full Cured:	24 hours @ 25°C	
• VOC Values:	250 g/ ltr.	

Surface Preparation:

PRE-CLEANING:

- Remove all visible surface deposits such as grease, oils and soils with suitable detergent.
- Remove salt and other contaminants by using fresh water.

Painting System:

Primers: Jazeera Epoxy Zinc Phosphate Primer, Jazeera Epo-Mastic, Jazeera Marine Primer.

Topcoats: Jaz Anti-Fouling Classico (ESP).

Application Condition:

Temperature:

- Temperature during application should be more than (5°C).
- Surface temperature: at least (3°C) above dew point.
- Relative humidity: maximum 85%.

Technical Data Sheet
JAZ ANTI-FOULING CLASSICO (ESP)
JM-35004

Application Method and Thinning:

THINNER: "Jazeera Thinner 507".

Application Method	Airless Spray	Air Spray	Brush/Roller**
Thinning (by volume)*	(10-15)%	(35-45) %	(15-25) %
Nozzle Orifice	0.015-0.021"	1.5- 1.8 mm	N/A
Nozzle Pressure	15 MPa (2100psi)	43.5-87 psi	N/A
Spray Angle	40-80°	50-80°	N/A

* Depends on the weather condition at work place.

** Recommended for stripe coat and small areas.

Film Thickness and Spreading Rate:

	Minimum		Maximum		Recommended	
	(μ m)	mil	(μ m)	mil	(μ m)	mil
Dry Film Thickness (DFT)	75	3	150	6	100	4
Wet Film Thickness (WFT)	142	5.7	283	11.3	189	7.6
	m ² /l	ft ² /USgal	m ² /l	ft ² /USgal	m ² /l	ft ² /US gal
Theoretical Spreading Rate	7.7	310	3.9	155	5.8	233

Drying Time and Recoating:

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly.

Temperature	25°C/77°F
Relative Humidity	50%
Surface Dry	2 hours
Hard Dry	7 hours
Dry to recoat, minimum	9 hours
Dry to recoat, maximum*	-----

Note: All records given in the table are typical at: Recommended film thickness, good ventilation and one coat system.

*The surface should be dry and clean prior to application.

The best time to recoat is before previous coat is cured. If this time is exceeded, the surface may need to be roughened slightly.

Packing:

- Packed in: Gallon 3.6 ltr

Shelf Life & Storage:

- Shelf life : 12 months @ 25 °C.
- Storage: The container should be kept in sealed, dry, cool, well ventilated place and stored in accordance with national regulations.

Technical Data Sheet
JAZ ANTI-FOULING CLASSICO (ESP)
JM-35004

Handling and Safety:

- Clean up: Use "Jazeera Thinner 507" for tools cleaning and in case of spillage, absorb and dispose.
- Handling: Handle with care. Stir very well before use.
- Health and safety: Please read and follow the precautionary notices displayed on the container, and all caution statements on the MSDS of this product. During application of paint, contact of liquid paint with eyes, skin, inhalation of paint mist and paint vapor should be strongly avoided. For spray application systems; applicator should wear protective clothing, gloves, also eye, skin and respiratory protection are always recommended. Keep away from reach of children.
- Ventilation: When used in enclosed areas, thorough air circulation must be used during and after application until the coating is cured. In addition, respirators must be used by all applicator.
- Caution: This product contains flammable solvents, keep away from sparks and open flame. For information on LEL and TLV, please read the MSDS.
- Environmental safety: Please donate the leftover paint and packaging to your local authorized institution for usage or recycling purpose.
- Note: Wastes and empty containers should be disposed of in accordance with local regulations made under the Control of Pollution Act and the Environmental Protection Act.

Disclaimer:

To the best of our knowledge the technical data listed herein is true and accurate up to publication date and is subject to change without prior notice. User must contact Jazeera Paints Company to verify of any modifications before specifying or ordering the product. Thus, information given in this sheet is not intended to be exhaustive and any person using the product other than the recommendations in this sheet or without reverting to our Jazeera TSD, he should take his accountability in this connection. As we are not capable to control the quality and the substrate's conditions as well as the factors that affect on using, or applying the product, so we never give any written or implied guarantee in these documents, but we guarantee our products to conform to Jazeera quality while we assume no responsibility for coverage, performance or injuries resulting from application. Liability "if any" is limited to replace the products mentioned above.