

## Technical Data Sheet

### Jazeera Fluorescent Clear

#### JA-18012

#### Description:

A water based, fast drying, acrylic clear topcoat specially formulated to provide long lasting protection for " Al-Jazeera Afrw Fluorescent". This coating is designed for use as a topcoat on painted signs .

#### Recommended Use:

Recommended to use as a protective topcoat on "Jazeera Afrw Fluorescent".

#### Characteristics:

- Specially designed to withstand the harsh weather conditions of the Middle East.
- Excellent resistance to UV.
- Excellent resistance to yellowing, oxidization, checking and cracking.
- Excellent dirt pick up resistance.
- High transparency.
- Good leveling.
- Long Lasting Protection.
- Easy to apply.

#### Physical Constants:

• Finish:	Glossy.	
• Colour:	Clear.	
• Specific Gravity:	1.05±0.02 at a temperature of 30°C	ASTM D-1475.
• Viscosity:	85±2 KU at a temperature of 30°C	ASTM D-562.
• Volume Solid:	26%	ASTM D2697.
• Theoretical Spreading Rate:	6.5 m <sup>2</sup> /ltr per coat at D.F.T. 40 µ. (To avoidwaste,be sure to buy the right amount of thepaint for the surface area required).	
• Sagging:	150 µ	ASTM D4400.
• Water Resistance:	Pass, 7 days	ASTM D870.
• Alkali Resistance:	Pass,7 days(1 % solution)	ASTM D1308.
• Salt Resistance:	Pass,7 days (1.5 % solution)	ASTM D1308.
• Adhesion:	Pass	ASTM D3359.
• Flexibility:	Pass, 6 mm. Diameter	ASTM D522.
Freeze-Thaw Stability:	Pass, 3 cycles	ASTM D2243.
Heater Stability:	Pass 49 days at 50°C.	

#### Surface Preparation:

New surfaces

- All new surfaces must be cured at least for 28 days prior to application of the primer.
- The surface must be treated by removing all forms release and protrusions to get a suitable surface for application.

For previously painted surfaces:

- Remove old paint from surfaces completely.
- Make sure that the surface is clean , dry , free from dust, oil, grease, salt and mold.

#### Application Guide:

- The surface must be removed from dust , grease, oil and other contaminants completely.
- The required temperature during application must not be less than 10°C; the surface moisture should not exceed 8% and therelative humidity at work place not to exceed 70%.
- Maximum pH of 9.
- Paint should be stirred carefully before use.
- Do not apply on wet and moistened surfaces until get completely dry.
- Do not apply the next coat unless the previous one is fully dry.Minimum recoating interval time should be given between the two coats.



## Technical Data Sheet Jazeera Fluorescent Clear JA-18012

---

### Application Tools:

- Spray gun: Recommended nozzle size: (1.5 – 1.8) mm.

### Thinner

- Tap water.

### Thining Ratio:

- 5-10%.

### Painting System:

- Apply one coat of Jazeera C Primer.
- Apply one coat of Jazeera Afrw Basecoat.
- Apply two coats of Jazeera Afrw Fluorescent .
- Apply two coats of Jazeera Afrw Fluorescent Clear.

### Drying Time:

- Surface dry 30 mins.
- Full dry 2 hrs.
- Over coating interval (minimum) 4 hrs.

All above results according to ASTM D5895 @25°C.

### Cleaning Tools:

- Tap water.

### Packing:

- Drum: 18L

### Shelf Life & Storage:

Shelf life : 24 months @ 25 °C.

Storage: The container should be kept in sealed, dry, cool, well -ventilated place and stored in accordance with national regulations.

### Safety Precautions:

- Please read and follow the precautionary notices displayed on the container, and all caution statements on the MSDS of this product.
- Handle with care before and during use.
- During application of paint, contact of liquid paint with eyes, skin, inhalation of paint mist and paint vapour, should be strongly avoided.
- Recommended to use the product in well-ventilated area when applying the paint in insufficient ventilated areas, forced ventilation should be provided.
- Keep away from the reach of children.

For environmental safety: please donate the leftover paint and packaging to your local authorized institution for usage or recycling purpose.

Note: Wastes and empty containers should be disposed of in accordance with local regulations made under the Control of Pollution Act and the Environmental Protection Act.

### Disclaimer:

To the best of our knowledge the technical data listed herein is true and accurate up to publication date and is subject to change without prior notice. User must contact Jazeera Paints Company to verify of any modifications before specifying or ordering the product. Thus, information given in this sheet is not intended to be exhaustive and any person using the product other than the recommendations in this sheet or without reverting to our Jazeera TSD, he should take his accountability in this connection.

As we are not capable to control the quality and the substrate's conditions as well as the factors that affect on using, or applying the product, so we never give any written or implied guarantee in these documents, but we guarantee our products to conform to Jazeera quality while we assume no responsibility for coverage, performance or injuries resulting from application. Liability "if any" is limited to replace the products mentioned above.