

**Technical Data Sheet**  
**JAZEERA URETHANE CLEAR**  
**J1-48032**

**Description:**

A high quality two-component clear gloss clear topcoat, based on polyurethane resin cured with aliphatic isocyanate for wood and steel surfaces, it has excellent resistance to yellowing, mar and UV.

**Recommended Use:**

For exterior and interior applications as a topcoat on steel and wooden surfaces such as doors, windows and furniture in a wide variety environment.

**Characteristics:**

- Excellent resistance to UV.
- Non-yellowing property.
- High mar resistance.
- Excellent gloss retention.
- Superior transparency.
- High flexibility.
- High resistance to water, chemicals and solvents.

**Physical Constants:**

• Finish:	Gloss	
• Color:	Clear	
• Volume Solid:	38%	ASTM D2697
• Specific Gravity:	0.96 (mixed Paint)	ASTM D1475
• DFT:	30 μm.	
• Theoretical Spreading Rate:	12.6 m <sup>2</sup> /L @ DFT 30 μm.	
• VOC Value:	555 g/L.	

**Surface Preparation:**

- Remove all visible surface deposits such as grease, oils, dust, soils, salt and other contaminants.
- Make the wooden surface smooth by sanding with sand paper and clean it well.
- Any damage areas in the primer should be prepared according to ISO 8504.

**Application Condition:**

- Temperature during application should be more than (5°C).
- Surface temperature: at least (3°C) above dew point.
- Relative humidity: maximum 85%.

**Application Data:**

Mixing ratio: By volume: Base Hardener  
4 : 1

Pot-life: 4 hours @ 25°C.

**Painting System:**

**Primers:**

- For wooden surfaces:
- For natural wood appearance, apply "Jazeera Polywood Sanding Sealer".
- For colored wood appearance, apply "Jazeera Wood Stain" before sealer.
- For steel surfaces: "Jazeera Epoxy Zinc Phosphate Primer", For other suitable primers consult Jazeera TSD.

**Topcoats:** Jazeera Urethane Clear.

**Technical Data Sheet**  
**JAZEERA URETHANE CLEAR**  
**J1-48032**

**Application Method and Thinning:**

Thinner: "Jazeera Thinner 507".

Application Method	Airless Spray	Air Spray	Brush/Roller**
Thinning (by volume)*	(0-3)%	(15-20)%	(5-10)%
Nozzle Orifice	0.015-0.021"	1.5- 1.8 mm	N/A
Nozzle Pressure	15 MPa ( 2100psi)	29.0-43.5psi	N/A
Spray Angle	40-80°	50-80°	N/A

\* Depends on the weather condition at work place.

\*\* Recommended for strip coat and small areas.

**Film Thickness and Spreading Rate:**

	Minimum		Maximum		Recommended	
	( $\mu$ m)	mil	( $\mu$ m)	mil	( $\mu$ m)	mil
Dry Film Thickness (DFT)	25	1.0	50	2	30	1.2
Wet Film Thickness (WFT)	66	2.6	131.5	5.3	79	3.16
	m <sup>2</sup> /l	ft <sup>2</sup> /USgal	m <sup>2</sup> /l	ft <sup>2</sup> /USgal	m <sup>2</sup> /l	ft <sup>2</sup> /US gal
Theoretical Spreading Rate	15.2	610	7.6	305	12.7	509

**Drying Time and Recoating:**

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly.

Temperature	25°C/77°F
Relative humidity	50%
Surface dry	30 min
Hard dry	2 hours
Dry to recoat, minimum	6 hours
Dry to recoat, maximum*	-----
Full cure	7 days

Note: All records given in the table are typical at: recommended film thickness, good ventilation and one coat system.

\*The surface should be dry and clean prior to application. The best time to recoat is before previous coat is cured. If this time is exceeded, the surface may need to be roughened slightly.

**Packing:**

- Packed in: Base Hardener
- Gallon 3 Ltr : 0.75 Ltr

**Shelf Life & Storage:**

- Shelf life : 12 months @ 25 °C.
- Storage: The container should be kept in sealed, dry, cool, well ventilated place and stored in accordance with national regulations.

**Technical Data Sheet**  
**JAZEERA URETHANE CLEAR**  
**J1-48032**

---

**Handling and Safety:**

- Clean up: Use "Jazeera Thinner 507" for tools cleaning and in case of spillage, absorb and dispose.
- Handling: Handle with care. Stir very well before use.
- Health and safety: Please read and follow the precautionary notices displayed on the container, and all caution statements on the MSDS of this product. During application of paint, contact of liquid paint with eyes, skin, inhalation of paint mist and paint vapor should be strongly avoided. For spray application systems; applicator should wear protective clothing, gloves, also eye, skin and respiratory protection are always recommended. Keep away from reach of children.
- Ventilation: When used in enclosed areas, thorough air circulation must be used during and after application until the coating is cured. In addition, respirators must be used by all applicator.
- Caution: This product contains flammable solvents, keep away from sparks and open flame. For information on LEL and TLV, please read the MSDS.
- Environmental safety: Please donate the leftover paint and packaging to your local authorized institution for usage or recycling purpose.
- Note: Wastes and empty containers should be disposed of in accordance with local regulations made under the Control of Pollution Act and the Environmental Protection Act.

**Disclaimer:**

To the best of our knowledge the technical data listed herein is true and accurate up to publication date and is subject to change without prior notice. User must contact Jazeera Paints Company to verify of any modifications before specifying or ordering the product. Thus, information given in this sheet is not intended to be exhaustive and any person using the product other than the recommendations in this sheet or without reverting to our Jazeera TSD, he should take his accountability in this connection. As we are not capable to control the quality and the substrate's conditions as well as the factors that affect on using, or applying the product, so we never give any written or implied guarantee in these documents, but we guarantee our products to conform to Jazeera quality while we assume no responsibility for coverage, performance or injuries resulting from application. Liability "if any" is limited to replace the products mentioned above.