

Technical Data Sheet

JAZEERA ROOF PROTECTION

JA-14001

Description:

A high performance elastomeric waterproof coating for roofs, based on acrylic emulsion. It has an excellent elasticity and water resistance properties.

Recommended Use:

Recommended to use for exterior applications as a protective coat over concrete and cement, mosaic tiles (terrazzo), steel, galvanised steel and polyurethane foam roofs of warehouses, residential, educational institutions and commercial buildings.

Characteristics:

- High resistance to water leakage.
- Breathable, allow the surface to breath (moisture).
- High elongation and crack bridging properties.
- Excellent adhesion to the surfaces.
- Excellent resistance to harsh Middle East weather conditions.

Certificats:

- Complies with the SASO standard 2627/2018

Physical Constants:

• Finish	Semi-Gloss with smooth touch.	
• Color	White.	
• Specific Gravity	1.20 At 25°C	ASTM D1475.
• Viscosity	3.20 x 1000 mPas at 40°C.	
• Volume solid	48 %	ASTM D2697.
• D.F.T.	0.5 mm each coat. Depends on the nature of the surfaces and application conditions.	
• Theoretical Spreading rate	0.96 m ² / Ltr. @ D.F.T 0.5 mm.	
• Water Vapor Transmition	14 gm / m ² / 24hrs.	ASTM D1653
• Weather Resistance	1500 hrs.	ASTM G154
• Water Resistance	Pass, 30 days, ASTM D870.	
• Alkali Resistance	Pass, 30 days (1 % solution).	ASTM D1308.
• Salt Resistance	Pass, 30 days (1 % solution).	ASTM D1308.

(to avoid waste, be sure to buy the right amount of the paint for the surface area required).

Surface Preparation:

For cement Tiles:

- The surface must be clean, dry, free from dust, oil, grease, salt, mold and protrusions.

For concrete and masonry surfaces:

- The concrete must be fully cured for 28 days.
- The surface must be treated by removing all forms release agent and protrusions to get a suitable surfaces for application.
- Make sure that the surface is sound, clean, free from dust, oil, greases, salt and mold.
- Fill cracks and holes by "Jazeera Epoxy Crack Filler 400".

For steel surfaces:

- The surface must be sound, clean, dry, free from corrosion, dust, oil, grease and salt
- "Jazeera Epo-mastic" should be applied on the rusted areas after suitable preparation.
- All holes shall be filled by suitable sealant.

For polyurethane foam surfaces:

- The surface must be clean, dry and free from dust, oil, grease, salt and mold.

Application Condition:

- The required temperature during application, must not be less than 5°C; the surface moisture should not exceed 8% and the relative humidity at work place should not exceed 70%.
- The Paint should be stirred well before use.
- Do not apply on wet and moistened surfaces until get completely dry.
- Do not apply the next coat unless the previous one is fully dry. Minimum recoating interval time should be given between the two coats.



Technical Data Sheet

JAZEERA ROOF PROTECTION

JA-14001

Application Tools:

- Airless spray: Nozzle Orifice : "0.017-0.021"
Nozzle Pressure : 15 MPa (2100psi)
Spray Angle : 40-60°
- Roller : (Recommended type: Dekor Nardeen 8009 - code:1093)
- Brush for narrow areas

Thinner:

- Recommended thinner is "Tap Water".

Painting System:

For concrete surfaces:

- Apply one coat of "Jazeera Roof Protection" as a primer after thinning (30-40)% by using roller.
- Apply two coats of "Jazeera Roof Protection" 500μ by roller.
- For best results, "Jazeera Tietex" mish can be used for reinforcing and also on corners, pipes and drainage.

For mozaic tiles surfaces:

- Apply one coat of "Jazeera Roof Protection" as a primer after thinning (30-40)% by using roller.
- Install "Jazeera Tietex" mish by using "Jazeera Roof Protection" on corners, pipes and drainage.
- Apply one coat of "Jazeera Roof Protection" 500μ by roller after that install "Jazeera Tietex" mish then apply another coat of "Jazeera Roof Protection" 500μ by roller and continue for full area.

For steel surfaces:

- Apply one coat of "Jazeera Roof Protection" thickness 75μ as a primer after thinning (10-15)% by using airless spray.
- Install "Jazeera Tietex" mish by using "Jazeera Roof Protection" on steel sheets joint which in the path of drainage water.
- Apply two coats of "Jazeera Roof Protection" 500μ by airless spray.

For polyurethane foam surfaces:

- Install "Jazeera Tietex" mish by using "Jazeera Roof Protection" on corners and big holes.
- Apply two coats of "Jazeera Roof Protection" 500μ by roller.

Instruction of Use:

- The density of fabric mesh shall be 93 gm/sq meter and elongation 40%.
- "Jazeera Rebond 100" must be used with sand and cement for repairing corners till getting surface free from sharp angles.
- Overlapping between the fabric should be 5-10 cm.
- The surface must be leveled to obtain uniform thickness after application.
- In case of maintenance works performed the damage areas must be cutted and repaired by using "Jazeera Roof Protection" and fabric Mesh with commitment to smoothing the feathering areas and overlapping (5-10) cm between new and old application.

Drying Time:

Surface dry:	4 hours.
Hard dry:	72 hours.
Recoating Interval	36 hours (minimum).
Full cure:	7 days.

All above test results according to ASTM D5895 @25°C.

Cleaning Tools:

Tap Water.

Packing:

- US Gallon.
- Drum 18 L.

Technical Data Sheet
JAZEERA ROOF PROTECTION
JA-14001

Shelf Life & Storage:

Shelf life : 24 months @ 25 °C.

Storage: The container should be kept in sealed, dry, cool, well -ventilated place and stored in accordance with national regulations.

Safety Precautions:

Please read and follow the precautionary notices displayed on the container, and all caution statements on the MSDS of this product.

- Handle with care before and during use. During application of paint, contact of liquid paint with eyes, skin, inhalation of paint mist and paint vapour, should be strongly avoided.
- When working with paint in in-sufficient ventilated areas, forced ventilation should be provided.
- For spray application system, eye, skin, respiratory protection are always recommended.
- Keep away from the reach of children.
- For environmental safety: please donate the leftover paint and packaging to your local authorized institution for usage or recycling .

Note: Wastes and empty containers should be disposed of in accordance with local regulations made under the Control of Pollution Act and the Environmental Protection Act.

Disclaimer:

To the best of our knowledge the technical data listed herein is true and accurate up to publication date and is subject to change without prior notice. User must contact Jazeera Paints Company to verify of any modifications before specifying or ordering the product. Thus, information given in this sheet is not intended to be exhaustive and any person using the product other than the recommendations in this sheet or without reverting to our Jazeera TSD, he should take his accountability in this connection.

As we are not capable to control the quality and the substrate's conditions as well as the factors that affect on using, or applying the product, so we never give any written or implied guarantee in these documents, but we guarantee our products to conform to Jazeera quality while we assume no responsibility for coverage, performance or injuries resulting from application. Liability "if any" is limited to replace the products mentioned above.