

Technical Data Sheet
JAZEERA FANTAZY
JA-36001

Description:

A high quality slow drying decorative paint, based on synthetic resin, characterized by high durability and exceptional fantastic appearance.

Recommended Use:

Recommended to use for interior applications on concrete, cement, gypsum and brick surfaces for houses, hotels and celebration halls.

Characteristics:

- Gives spaces a distinctive decorative effect.
- Allows sufficient drying time to achieve the desired design.
- Excellent adhesion and high durability.
- Available in a wide range of colors.

Physical Constants:

• Finish	Semi-gloss.	
• Color	As per Jazeera color card.	
• Specific Gravity	0.9	ASTM D1475.
• Viscosity	84 KU	ASTM D562.
• Volume Solid	30 %.	ASTM D2697.
• DFT	Varies according to method of application	
• Theoretical Spreading Rate*	Depends on the nature of the surface and application system	
• Flash Point	39°C.	

*The practical spreading rate of the product depends on the surface, ambient temperature, application method, actual DFT and the wasted amount. (To avoid waste, be sure to buy the right amount of the paint for the required surface area)

Surface Preparation:

- All new concrete surfaces must be cured at least for 28 days prior to application of the primer.
- For previously painted surfaces remove old paint completely.
- The substrate should have sufficient strength and free from unsounded areas, pug holes, protrusions and pops.
- Make sure that the surface is clean , dry , free from dust, oil, grease, salt , mold and all forms release agents /curing.
- Fill the holes and cracks with suitable fillers "Jazeera Ultimate", "Jazeera Unique Filler" and "Jazeera Epoxy Crack Filler 400" prior to application of the primer (Refer to TSD).

Application Guide:

1. The required temperature during application, must not be less than 5°C; the surface moisture should not exceed 8% and the relative humidity at work place should not exceed 70%.
2. pH of surface should not exceed 9.
3. Paint should be stirred carefully before use.
4. A suitable quantity of "Jazeera Thinner 504" can be added to get reasonable viscosity for application.
5. Do not apply on wet and moistened surfaces until completely dry.
6. Do not apply the next coat unless the previous one is fully dry. Minimum recoating interval time should be followed.
7. Adequate ventilation should be provided during application.

Application Tools:

Brush: suitable type.
Roller: soft and wooden type.
Any other special tools can be used for desired pattern.

Thinner:

"Jazeera Thinner 504"



Technical Data Sheet
JAZEERA FANTAZY
JA-36001

Thinning Ratio:

- (10 - 15)% by volume, Depends on weather and application conditions.

Painting System:

- Apply one coat of "Jazeera Green Prime".
- Apply two coats of "Jazeera Green Putty".
- Apply two coats of "Jazetal Semigloss" and allow it for full drying.
- Apply one coat of "Jazeera Fantazy".
- The desired decorative design is formed during the surface drying time.

Drying Time:

Surface dry:	3 hours.
Hard dry:	12 hours.
Full cure	7 days.

All above test results according to ASTM D5895 @25°C.

Cleaning Tools:

"Jazeera Thinner 504"

Packing:

Can 1 L.

Storage and Shelf Life:

Shelf life: 24 months @ 25 °C.

Storage: The container should be kept in sealed, dry, cool, well-ventilated place and stored in accordance with national regulations.

Safety Precaution:

Please read and follow the precautionary notices displayed on the container, and all caution statements on the MSDS of this product.

- Handle with care before and during use.
- During application of paint, contact of liquid paint with eyes, skin, inhalation of paint mist and paint vapour, should be strongly avoided.
- Recommended to use the product in well-ventilated area when applying the paint in insufficient ventilated areas, forced ventilation should be provided.
- Keep away from the reach of children.

For environmental safety: please donate the leftover paint and packaging to your local authorized institution for usage or recycling purpose.

Disclaimer:

To the best of our knowledge the technical data listed herein is true and accurate up to publication date and is subject to change without prior notice. User must contact Jazeera Paints Company to verify of any modifications before specifying or ordering the product. Thus, information given in this sheet is not intended to be exhaustive and any person using the product other than the recommendations in this sheet or without reverting to our Jazeera TSD, he should take his accountability in this connection.

As we are not capable to control the quality and the substrate's conditions as well as the factors that affect on using, or applying the product, so we never give any written or implied guarantee in these documents, but we guarantee our products to conform to Jazeera quality while we assume no responsibility for coverage, performance or injuries resulting from application. Liability "if any" is limited to replace the products mentioned above.